

DYNA-GLOSS (22.5%)

Technical Data Sheet

LOW MAINTAINANCE FLOOR FINISH

DESCRIPTION:

DYNA-GLOSS (22.5%) is a metal cross-linked hard floor finish that yields a hard anti-scuff film that can be easily repaired when necessary. New technology has allowed DYNA-GLOSS (22.5%) to achieve excellent results with less maintenance. DYNA-GLOSS (22.5%) has a diamond like gloss and excellent durability with minimal mop drag during application. DYNA-GLOSS (22.5%) dries in 30 minutes or less under normal conditions (Ambient temperature and humidity may affect drying time).

USES:

For use on vinyl tile, vinyl composition tile (VCT), asphalt, rubber terrazzo and all sealed masonry surfaces. Specifically designed for the retail industry when a low maintenance program is desired.

SOLIDS	22.5% ± 0.5%
pH	8.6 ± 0.2%
COLOR	Milk White
DENSITY	8.50 #/gal
FLAMMABILITY	Non-Flammable
SHELF LIFE	1 year
STABILITY	Passes 3 Freeze Thaw Cycles per ASTM D3209-82

LIQUID PROPERTIES:

FILM PROPERTIES:

CLARITY	Clear
COLOR	Colorless
COLOR STABILITY	Non-yellowing, U.V. tested for 72 hours
GLOSS	88 min per ASTM D1455-82
SLIP RESISTANCE	Meets or exceeds ASTM D2047-82

DIRECTIONS:

- 1 Clean or strip area to be coated.
- 2 Rinse floor thoroughly and allow to dry.
- 3 Apply 4-6 medium coats using cross coat technique. Allow to dry for 20 to 30 minutes between coats.

MAINTENANCE

- 1 Sweep or dry mop the area to be maintained.
- 2 Mop or autoscrub using a NEUTRAL FLOOR CLEANER or FLOOR MAINTAINER.
- 3 Burnish floor.
- 4 Recoat as necessary.

COVERAGE:

2,000 to 2,500 square feet per gallon.

CAUTIONS:

Contains Diethylene glycol ethyl ether CAS#111-90-0

Wear rubber gloves and eye protection when using this product.

KEEP OUT OF THE REACH OF CHILDREN

EMERGENCY ACTIONS:

If ingested, induce vomiting. Seek medical attention at once!

If eye is contacted, flush with water and seek medical help.

For external skin contact, remove contaminated clothing and wash thoroughly with water.



DYNASOL
330 Pine St. Canton, MA 02021
781-821-8888