

# FIRST IMPRESSION

## Technical Data Sheet

### HIGH SPEED FLOOR FINISH

#### DESCRIPTION:

FIRST IMPRESSION (22.5%) is a metal crosslinked, high speed floor finish comprised of four thermally activated polymers that yield a hard, anti-scuff floor finish that can be easily repaired yet has excellent durability, high initial gloss and black mark resistance. New technology has allowed FIRST IMPRESSION to have minimal mop drag and to dry in the same time as do lower solids finishes.

#### USES:

For use on vinyl, vinyl composition, asphalt, rubber terrazzo and all sealed masonry surfaces.

#### LIQUID PROPERTIES:

SOLIDS	22.5.0% ± 0.5%
pH	8.6 ± 0.2%
COLOR	Milk White
DENSITY	8.80 #/gal
FLAMMABILITY	Non-Flammable
SHELF LIFE	1 yr @ 22°C, 45 days @ 50°C
STABILITY	Passes 3 Freeze Thaw Cycles per ASTM D3209-82

#### FILM PROPERTIES:

CLARITY	Clear
COLOR	Colorless
COLOR STABILITY	Non-yellowing, U.V. tested for 72 hours
GLOSS	88 min per ASTM D1455-82
SLIP RESISTANCE	Meets or exceeds ASTM D2047-82

#### DIRECTIONS:

- 1 Clean or strip area to be coated.
- 2 Rinse floor thoroughly and allow to dry.
- 3 Apply 3-4 medium coats using cross coat technique. Allow to dry for 20 minutes between coats.

#### MAINTENANCE

- 1 Sweep or dry mop the area to be maintained.
- 2 Mop or Autoscrub floor with HIGHLIGHT NEUTRAL or other Spectrowax Maintainer.
- 3 Burnish floor.
- 4 Recoat as necessary.

#### COVERAGE:

2,000 to 3,000 square feet per gallon.

#### CAUTIONS:

Contains Diethylene glycol ethyl ether CAS#111-90-0, Dipropylene Glycol Methyl Ether CAS#34590-94-8

Wear rubber gloves and eye protection when using this product.


#### KEEP OUT OF THE REACH OF CHILDREN

#### EMERGENCY ACTIONS:

If ingested, induce vomiting. Seek medical attention at once!

If eye is contacted, flush with water and seek medical help.

For external skin contact, remove contaminated clothing and wash thoroughly with water.



490A Constitution Drive  
Taunton, MA 02780  
1-866-878-9100